# 8617A



## **Premium Thermal Paste, 3 W/(m·K)**

8617A is a silicone-free thermal grease with very high thermal conductivity and exceptional wetting properties. The thixotropic paste conforms to the intricate geometry at the component/heatsink interface while avoiding bleed and pump out. Its wide operating temperature range allows high heat dissipation and thermal cycling stability. Once applied, circuits can be powered immediately.

This thermal paste is often used as a gap filler on heatsinks to CPUs, LEDs, and other electronic components. Its high thermal conductivity makes it ideal for energy-intensive devices like thermal sensors, IGBTs, thermal wells and power resistors.



- 1-part compound
- Silicone-free—will not contaminate surfaces
- Wide operating temperature, ideal for aggressive thermal cycling conditions
- Low bond line thickness

### **Available Packaging**

Cat. No.	Packaging	Net Vol.	Net Wt.
8617A-3ML	Syringe	3 mL	8.10 g
8617A-10ML	Syringe	10 mL	27.0 g
8617A-85ML	Tube	85 mL	229 g
8617A-300ML	Cartridge	300 mL	810 g

#### **Contact Information**

MG Chemicals, 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772

International: +(1) 905-331-1396 Europe: +(44)1663 362888



### **Properties**

Color	White	
Density	2.7	g/mL
Viscosity	220	Pa⋅s
Resistivity	1014	$\Omega {\cdot} cm$
Thermal Conductivity @ 25 °C	3.0	$W/(m \cdot K)$
Thermal Resistance	0.01	$^{\circ}\text{C-in}^2/\text{W}$
Breakdown Voltage	16	kV
Dissipation Factor @ 1 kHz	0.017	
Service Temperature Range	-55–200	°C

## **Storage and Handling**

Store between 16 and 27 °C in a dry area, away from sunlight (see SDS).

#### **Disclaimer**

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.